

Armafinish® 99

THE ELASTIC PAINT DESIGNED FOR
PROTECTION AND COVERING OF
ARMAFLEX®



- Resistant to weathering and ageing. Coating remains elastic
- Drip-free paint
- Protection of Armaflex® insulation materials

Technical Data - Armafinish 99

| | |
|------------------------------|---|
| Brief description | Armafinish 99 is a paint, which remains permanently elastic, is resistant to weathering and has good ageing resistance. |
| Material type | Non-drip |
| Colour | white (RAL 9001) or grey (RAL 7037) |
| Material Special Information | Normal consumption: 0,55 l/m ² when two coats are applied (corresponds to a dry film thickness of 0,26mm). |
| Applications | Protection of Armaflex insulation materials when installed outdoors and for marking purposes for interior use. |
| Assembly | All Armaflex insulation (except HT/Armaflex and Armaflex products based on Armaprene), see relevant product data sheet) which is installed outdoors must be covered with two complete coats of Armafinish 99. Application temperature: + 10 °C to + 30 °C, maximum relative humidity 80%. Drying time at + 20 °C: approx. 2 hours. It is also necessary to allow this time between coats; the second coat must be applied within 7 days. Paint may be applied using a brush or roller. Clean tools with water. |
| Remarks | Unprotected Armaflex must not be exposed to weathering for more than 3 days, so the paint should be applied as soon as possible. The protective coating should be inspected at regular intervals. After 2 years at the latest, two further coats should be applied. Refer to special instruction / safety data sheet. |

| Property | Value/Assessment | Special Remark |
|--------------------------|---|---|
| Other technical features | | |
| Storage & Shelf life | Shelf-life in unopened container: 12 months. | Keep container tightly closed and store in a cool, well ventilated and frost-free place. |
| Explosion limits | Lower: none Upper: none | |
| Hazard Class | Environmentally hazardous substance as defined by the transport regulations (ADR/RID, IMDG-Code, ICAO-TI/IATA-DGR). | |
| Recycling | Allocation of a waste code number, according to the European Waste Catalogue, should be carried out in agreement with the regional waste disposal company. More details see relevant Safety Data Sheet. | Packaging must be emptied of all residues. Packaging with traces of cured product can be recycled. Packaging with uncured product must be disposed of in the same manner as the medium. |

All data and technical information are based on results achieved under typical application conditions. Recipients of this information should, in their own interest and responsibility, clarify with us in due time whether or not the data and information apply to the intended application area. Installation instructions are available in our Armaflex installation manual.

Armafinish 99 paint



| Code | Article description | Pieces/carton |
|-----------------------|---|---------------|
| AS-PAINT2.5LW | Armafinish paint 99, white, 2.5 litre cans | 4 |
| FINISH/GY-2,5 | protective coat for Armaflex, silver grey (RAL-Nr. 7037), 2,5 liter buckets | 4 |
| FINISH/GY-2,5N | protective coat for Armaflex, silver grey (RAL-Nr. 7037), 2,5 liter buckets | 4 |
| FINISH/WH-2,5 | protective coat for Armaflex, white (RAL-Nr. 9001), 2,5 liter buckets | 4 |
| FINISH/WH-2,5N | protective coat for Armaflex, white (RAL-Nr. 9001), 2,5 liter buckets | 4 |